# TECHNICAL DATASHEET PTF DUSTED



Utrecht, 1 augustus '19

### ETCH GLASS PTA/PTAS/PTF SERIES ASP26 PERMANENT WK120

#### Face Material

Self-adhesive material for plotter. Polymeric translucent vinyl with metallic flakes.

Type Translucent polymeric vinyl Colour and Finish Weight 100 g/m $^2$  ±10% ISO-536 Thickness 80  $\mu$  ±10% ISO 534-80

#### Adhesive

Permanent solvent acrylic featuring high cohesion and good water resistance.

Reference ASP26 permanent Type Acrylic permanent

Min. Appl. Temp. +10°C Service Temp. -20°C/+130°C

Shear High

Tack Medium N/inch²
Final Adhesion High N/inch

#### Liner

Type One side siliconised clay coated

Kraft

Colour and Finish White

Weight 120 g/m<sup>2</sup> PP-032 - ISO

±10% 536

Thickness 108  $\mu$  ±10% ISO 534 Transparency n.a. % DIN 53 147-64

## **Applications**

Translucent Etch simulation effect for glass decoration. 5 years outdoor durability. Durability is given in good faith based on simulated weathering tests and real life vertical exposure in non-extreme mid-European conditions.

#### **Printing Methods**

Not printable.

Testing for suitability between media, printers and inks is always recommended prior to use.

#### Shelf life

24 months

which has not undergone further processing, under the following STORAGE CONDITIONS:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- · Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- . Do not expose to direct sunlight or heat sources.